

---

**LX-00140 RAL 7044 GRAY SURE FOOT ENAMEL**

<b>Description:</b>	A tough, rugged, abrasion resistant alkyd floor coating for interior and exterior use on concrete, wood and metal surfaces.	
<b>Uses:</b>	Excellent for use on floors, steps, and ramps in heavy traffic areas and for industrial maintenance where durability and washability are important.	
<b>Vehicle Type:</b>	Alkyd	
<b>% Solids by Volume:</b>	58.05% ± 2%	
<b>% Solids by Weight:</b>	80.52% ± 2%	
<b>Viscosity @ 77°F:</b>	110 - 120 KU	
<b>Weight per Gallon:</b>	14.09 Lbs/Gal	
<b>V.O.C.:</b>	2.74 Lbs/Gal	
<b>Recommended Film Thickness:</b>	3 - 4 mils DFT	Coverage: 250 - 300 sq ft.
<b>Theoretical Coverage:</b>	928.8 Sq Ft/Gal @ 1 mil	
<b>Sheen:</b>	Flat	
<b>Drying Time @77°F:</b>	To touch: 1 ½ hrs.	
<b>Solvent:</b>	Aliphatic Hydrocarbons	
<b>Thinning:</b>	Not recommended but if necessary use mineral spirits.	
<b>Flash Point:</b>	105°F	
<b>Application:</b>	Brush or roll recommended.	
<b>Compliant to:</b>	OTC (Ozone Transport commission) requirements FDA (Incidental food contact) requirements Rule 66	

Continues on back....

<b>Limitations:</b>	Apply only in good weather. Do not apply unless air, surface, and material temperature are at least 50° (10°C). Do not apply unless surface temperature is at least 5°F (3°C) above the dew point or when it is likely that moisture will contact surface of wet film. Do not use in immersion or high temperature service.
<b>Surface Preparation:</b>	Clean surface carefully. Remove dirt, grease, rust, old paint and other foreign materials by wire brushing, chipping or scraping. Wash surface with detergent solution, rinse thoroughly with clear water & allow to dry. New or dense concrete surfaces must be etched to insure proper bonding. After cleaning, rinse with a solution of zinc sulphate (2 ½ lbs. per gallon of water) or muriatic acid (3%). Allow to dry without rinsing.
<b>Mixing:</b>	Paint should be mixed as necessary to insure homogeneity.
<b>Shelf Life:</b>	Once opened 6 months in containers. In general, unopened paint will have a shelf life exceeding one year.
<b>Safety:</b>	This product and recommended thinners contain solvents and/or other chemical ingredients. Please observe proper health and safety procedures during storage, handling, application and drying periods. For optimum safety, user is directed to consult the current Material Safety Data Sheet for this product and other products being used coincidentally. When using in a confined area, consult the current OSHA or ANSI bulletins on safety requirements.

LX-00140 041718 TC  
H/USERS/WP51/PDSLX

The technical data furnished herein is accurate to the best of our knowledge and we guarantee our products to conform to Davis-Frost quality control. However, we can assume no liability for our products' coverage, performance or suitability for end use, since these factors are beyond our control. Neither can we assume liability for damages, injury or delays resulting from use of Davis-Frost materials. Liability, if any, is limited to replacement of defective materials or to a monetary value not to exceed the purchase price of materials. Technical data is subject to change